

12NiCrMo13-6* All

General Information

12NiCrMo13-6* or 9313 as it is also named in US standards is a case hardening steel used in forgings to eg rock drilling tools.

For additional Heat Treatment Data, please visit the Heat Treatment Guide.

** Designation followed by "*" is not an official EN standard grade but named according to the rules in EN 10027.*

Similar designations

AISI 9313

Chemical composition

Variant	Cast	Weldability		C%	Si%	Mn %	P%	S%	Cr%	Ni%	Mo%	Cu%
254R	IC	CEV 0.8 _{max}	Min	0.11	0.20	0.65	-	-	1.40	3.15	0.10	-
		Pcm 0.33 _{max}	Max	0.15	0.26	0.75	0.010	0.005	1.50	3.35	0.14	0.25
4708	CC	CEV 0.76 _{max}	Min	0.11	0.20	0.60	-	-	1.35	3.15	0.10	-
		Pcm 0.3 _{max}	Max	0.14	0.35	0.70	0.015	0.015	1.45	3.35	0.14	0.25

Mechanical Properties

Variant

$R_{p0.2}$ * R_{eh} , ** R_{el}

Transformation temperatures

	Temperature °C
MS	386
AC1	693
AC3	806

Other properties (typical values)

Youngs module (GPa)	Poisson´s ratio (-)	Shear module (GPa)	Density (kg/m3)
210	0.3	80	7800
Average CTE 20-300°C (µm/m°K)	Specific heat capacity 50/100°C (J/kg°K)	Thermal conductivity Ambient temperature (W/m°K)	Electrical resistivity Ambient temperature (µΩm)
12	460 - 480	40 - 45	0.20 - 0.25

Contact us

Would you like to know more about our offers? Don´t hesitate to contact us:

Via e-mail: info@ovako.com

Via telephone: +46 8 622 1300

For more detailed information please visit <http://www.ovako.com/en/Contact-Ovako/>

Disclaimer

The information in this document is for illustrative purposes only. The data and examples are only general recommendations and not a warranty or a guarantee. The suitability of a product for a specific application can be confirmed only by Ovako once given the actual conditions. The purchaser of an Ovako product has the responsibility to ascertain and control the applicability of the products before using them. Continuous development may necessitate changes in technical data without notice. This document is only valid for Ovako material. Other material, covering the same international specifications, does not necessarily comply with the properties presented in this document.