

16MnCr5 All

General Information

16MnCr5 is an alloyed case hardening steel used for e.g. mechanical engineering components. The steel can be M-treated in order to optimize the machinability.

For additional Heat Treatment Data, please visit the Heat Treatment Guide.

Similar designations

16MnCrS5, EN ISO 683-17, 17MnCr5, 1.7131, 1.7139, 1.3521

Chemical composition

Variant	Cast	Weldability		C%	Si%	Mn%	P%	S%	Cr%	Ni%	Mo%	V%	Cu%
234K	IC	CEV 0.69 _{max}	Min	0.14	0.15	1.05	-	0.015	0.85	-	-	-	-
		Pcm 0.36 _{max}	Max	0.19	0.35	1.30	0.020	0.025	1.10	0.20	0.10	0.100	0.20
En ISO 683-3	Std	CEV _{max}	Min	0.14	0.15	1.00	-	-	0.80	-	-	-	-
		Pcm _{max}	Max	0.19	0.40	1.30	0.025	0.035	1.10	-	-	-	0.40

Mechanical Properties

Variant	Condition ^①	Format	Dimension [mm]	Hardness
234K	+U	All formats	24 < 190	230 HB typical
	+A	All formats	24 < 190	207 HB typical
	+FP	All formats	24 < 190	140-187 HB

$R_{p0.2}$ * R_{eh} , ** R_{el}


Transformation temperatures

	Temperature °C
MS	430
AC1	734
AC3	827

Heat treatment recommendations

Treatment	Condition ^①	Temperature cycle	Cooling/quenching
Hot forging	+U	850-1200°C	Slow or in air
Soft annealing	+A	670-710°C	Slowly (15°C/h) until 600°C
Annealing	+FP	Stage1: 950-1000°C, quickly to stage 2 Stage 2: 620-650°C	Hold for about 3h. Then cool in air
Normalizing	+N	860-890°C	In air
Stress relieve annealing	+SRA	600-680°C	In air
Carburizing	+C	880-980°C	In air
Quenching	+Q	860-900°C	In oil or water
Tempering	+T	150-200°C	In air

Hardenability



Other properties (typical values)

Youngs module (GPa)	Poisson's ratio (-)	Shear module (GPa)	Density (kg/m ³)
210	0.3	80	7800
Average CTE 20-300°C (µm/m°K)	Specific heat capacity 50/100°C (J/kg°K)	Thermal conductivity Ambient temperature (W/m°K)	Electrical resistivity Ambient temperature (µΩm)
12	460 - 480	40 - 45	0.20 - 0.25

Contact us

Would you like to know more about our offers? Don't hesitate to contact us:

Via e-mail: info@ovako.com

Via telephone: +46 8 622 1300

For more detailed information please visit <http://www.ovako.com/en/Contact-Ovako/>

Disclaimer

The information in this document is for illustrative purposes only. The data and examples are only general recommendations and not a warranty or a guarantee. The suitability of a product for a specific application can be confirmed only by Ovako once given the actual conditions. The purchaser of an Ovako product has the responsibility to ascertain and control the applicability of the products before using them. Continuous development may necessitate changes in technical data without notice. This document is only valid for Ovako material. Other material, covering the same international specifications, does not necessarily comply with the properties presented in this document.