

18CrNiMnMo7-5-5\* All

General Information

Ovako 250R is a quench and tempering steel that is used for large chains.

- Weldable using normal chain welding methods
- Available as bar in as rolled condition

*\* Designation followed by "\*" is not an official EN standard grade but named according to the rules in EN 10027.*

Chemical composition



| Variant | Cast | Weldability             |     | C %  | Si % | Mn % | P %   | S %   | Cr % | Ni % | Mo % | DI %  |
|---------|------|-------------------------|-----|------|------|------|-------|-------|------|------|------|-------|
| 250R    | IC   | CEV 1.01 <sub>max</sub> | Min | 0.17 | 0.20 | 1.15 | -     | -     | 1.70 | 1.15 | 0.42 | 0.00  |
|         |      | Pcm 0.44 <sub>max</sub> | Max | 0.19 | 0.30 | 1.30 | 0.015 | 0.010 | 1.90 | 1.30 | 0.48 | 10.50 |

Transformation  
temperatures


|     | Temperature °C |
|-----|----------------|
| AC1 | 726            |
| AC3 | 817            |

Heat Treatment Guide generated Graphs

The following graphs are generated from a theoretical model. For further info see the Heat treatment guide module. Select a specific grade version for individual display.




# Jominy






Ovako 250R



Hardenability of Ovako 250R calculated from CCT measurements and two-dimensional quenching of a bar.

CCT - Ovako 250R



|                      | A   | B   | C   | D   | E    | F&   |
|----------------------|-----|-----|-----|-----|------|------|
| t <sub>8-5</sub> [s] | 10  | 100 | 200 | 500 | 1000 | 2000 |
| Hv <sub>30</sub>     | 450 | 424 | 422 | 393 | 377  | 345  |

Steel cleanliness

| Micro inclusions - steel grade 250R |           |     |     |     |    |    |     | Macro inclusions - 250R |                                |
|-------------------------------------|-----------|-----|-----|-----|----|----|-----|-------------------------|--------------------------------|
| Applied standard                    | ASTM E45  |     |     |     |    |    |     | Applied standard        | ISO 3763<br>(Blue fracture)    |
| Sampling                            | ASTM A295 |     |     |     |    |    |     | Sampling                | Statistical testing on billets |
| Maximum average                     | A         |     | B   |     | C  |    | D   | Limits                  | < 5 mm/dm <sup>2</sup>         |
| limits                              | Th        | He  | Th  | He  | Th | He | Th  |                         |                                |
|                                     | 2.5       | 1.5 | 1.0 | 0.5 | 0  | 0  | 0.5 |                         |                                |

SUSTAINABILITY-ENVIRONMENTAL IMPACT DATA

At Ovako sustainability and reduction of our environmental impact is a major focus in everything we do.

Further information is found [here](#).

| Steel works | Hofors | Smedjebacken | Imatra |
|-------------|--------|--------------|--------|
| CO2e/kg     | 120    | 62           | 76     |

To get the full picture of our products environmental impact we have to look at all of our CO<sub>2</sub> emission sources.

Not only the steel work Scope 1-2 itself, but all operations downstream in our production, heating and heat treatment furnaces etc (full scope 1-2) as well as all the emission from input material, eg. alloys, scope 3.

| Steel Grade | Format    | Condition | Scope 1-3 (CO2e kg /1000 kg steel) | Climate compensated Net emission = Scope 3 (CO2e kg /1000 kg steel) Scope 1 - 2 = 0 (compensated) |
|-------------|-----------|-----------|------------------------------------|---|
| 250R        | Round bar | +AR       | 842                                | 443   |

All above data are to be seen as typical values for the specified format and condition. Detailed information about your specific product please contact your sales contact.

### Other properties (typical values)

| Youngs module (GPa)           | Poisson´s ratio (-)                       | Shear module (GPa)                               | Density (kg/m3)                                  |
|-------------------------------|---|--|--|
| 210                           | 0.3                                       | 80   | 7800   |
| Average CTE 20-300°C (µm/m°K) | Specific heat capacity 50/100°C (J/kg °K) | Thermal conductivity Ambient temperature (W/m°K) | Electrical resistivity Ambient temperature (µΩm) |
| 12                            | 460 - 480                                 | 40 - 45  | 0.20 - 0.25                                      |

### Contact us

Would you like to know more about our offers? Don´t hesitate to contact us:

Via e-mail: [info@ovako.com](mailto:info@ovako.com)

Via telephone: +46 8 622 1300

For more detailed information please visit <http://www.ovako.com/en/Contact-Ovako/>

### Disclaimer

*The information in this document is for illustrative purposes only. The data and examples are only general recommendations and not a warranty or a guarantee. The suitability of a product for a specific application can be confirmed only by Ovako once given the actual conditions. The purchaser of an Ovako product has the responsibility to ascertain and control the applicability of the products before using them. Continuous development may necessitate changes in technical data without notice. This document is only valid for Ovako material. Other material, covering the same international specifications, does not necessarily comply with the properties presented in this document.*