**OVAKO** 

# 18CrNiMo8-8\* A

# **General Information**

18CrNiMo8-8\* is a case hardening steel suitable for demanding powertrain applications and used in eg. diesel injection nozzles.

#### **Chemical composition**

Variant	Cast		С%	Si %	Mn %	Р%	S %	Cr %	Ni %	Mo %	Cu %
258D	IC	Min	0.16	0.15	0.45	-	0.016	1.85	1.85	0.95	-
		Max	0.20	0.35	0.60	0.025	0.023	2.10	2.10	1.15	0.25

# **Mechanical Properties**

Variant	Condition	Format	Dimension [mm]	Hardness
258D	+A	Round bar	< 55	250 HB typical

Rp<sub>0.2</sub> \* R<sub>eh</sub>, \*\* R<sub>el</sub>

# Heat Treatment Guide generated Graphs

The following graphs are generated from a theoretical model. For further info see the Heat treatment guide module. Select a specific grade version for individual display.



Tempering Diagram (hardness)





Tempering temperature (°C)

Jominy



# Hardenability



Jominy hardenability according to ASTM A255. Data is average value with +/- standard deviation.

# SUSTAINABILITY-ENVIRONMENTAL IMPACT DATA

At Ovako sustainability and reduction of our environmental impact is a major focus in everything we do.

Further information is found here.

Steel works	Hofors	Smedjebacken	Imatra
CO2e/kg	120	62	76

To get the full picture of our products environmental impact we have to look at all of our  $CO_2$  emission sources.

Not only the steel work Scope 1-2 itself, but all operations downstream in our production, heating and heat treatment furnaces etc (full scope 1-2) as well as all the emission from input material, eg. alloys, scope 3.

Steel Grade	Format	G Condition	Scope 1-3 (CO2e kg /1000 kg steel)	Climate compensated Net emission = Scope 3 (CO2e kg /1000 kg steel) Scope 1 - 2 = 0 (compensated)
258D	Round bar	+AR	997	598
258D	Round bar	+A	1005	603

To get the full picture of our products environmental impact we have to look at all of our  $CO_2$  emission sources.

Not only the steel work Scope 1-2 itself, but all operations downstream in our production, heating and heat treatment furnaces etc (full scope 1-2) as well as all the emission from input material, eg. alloys, scope 3.

# Other properties (typical values)

Youngs module (GPa)	Poisson's ratio (-)	Shear module (GPa)	Density (kg/m3)		
210	0.3	80	7800		
Average CTE 20- 300°C (µm/m°K)	Specific heat capacity 50/100°C (J/kg °K)	Thermal conductivity Ambient temperature (W/m°K)	Electrical resistivityAmbient temperature (μΩm)		
12	460 - 480	40 - 45	0.20 - 0.25		

### Contact us

Would you like to know more about our offers? Don't hesitate to contact us:

Via e-mail: info@ovako.com

Via telephone: +46 8 622 1300

For more detailed information please visit http://www.ovako.com/en/Contact-Ovako/

#### Disclaimer

The information in this document is for illustrative purposes only. The data and examples are only general recommendations and not a warranty or a guarantee. The suitability of a product for a specific application can be confirmed only by Ovako once given the actual conditions. The purchaser of an Ovako product has the responsibility to ascertain and control the applicability of the products before using them. Continuous development may necessitate changes in technical data without notice. This document is only valid for Ovako material. Other material, covering the same international specifications, does not necessarily comply with the properties presented in this document.