

## STEEL GRADE

Last revised: Thu, 16 Jan 2025 15:45:52 GMT

# 19MnVS6

All

## General Information

19MnVS6 according to EN10267 may with its generous chemical analysis and moderate mechanical requirements host a number of grades. It does at Ovako's! All variants are microalloyed with vanadium which gives a fine grain size and a good start for excellent toughness. The most frequent usage is as rolled, but all members in the family may be heat-treated in different ways. A heat-treatment will naturally affect the mechanical properties.

The Ovako program starts with a yield strength of minimum 400 MPa and finishes at minimum 520 MPa where each variant is carefully balanced to give the desired properties without a wasteful addition of alloying elements. Weldability goes from excellent to good with increasing alloying content and yield strength.

19MnVS6 is also available as M-steel.

## Similar designations

SB280 - 18Mn6, E470, SS2134, 1.5217, 19MnV6

## Chemical composition

Variant	Cast	Weldability		C %	Si %	Mn %	P %	S %	Cr %	Mo %	V %	N %
19MnVS6 EN10267:1998 (ref)	Std	CEV 0.5 <sub>max</sub>	Min	0.15	0.15	1.20	-	0.020	-	-	0.080	0.0100
		Pcm 0.31 <sub>max</sub>	Max	0.22	0.80	1.60	0.025	0.060	0.30	0.08	0.200	0.0200

## Mechanical Properties

Variant	Condition ⓘ	Format	Yield strength min [MPa]	Tensile strength [MPa]	Elongation A <sub>5</sub> [%]	Reduction of area Z <sub>min</sub> [%]
19MnVS6 EN10267:1998 (ref)	+AR	All formats	390*	600-750	16	32

*R<sub>p0,2</sub> \* R<sub>eh</sub>, \*\* R<sub>el</sub>*

## Transformation temperatures

	Temperature °C
MS	410
AC1	720
AC3	810

## SUSTAINABILITY-ENVIRONMENTAL IMPACT DATA

At Ovako sustainability and reduction of our environmental impact is a major focus in everything we do.

Further information is found [here](#).

Steel works	Hofors	Smedjebacken	Imatra
CO2e/kg	120	62	76

To get the full picture of our products environmental impact we have to look at all of our CO<sub>2</sub> emission sources.

Not only the steel work Scope 1-2 itself, but all operations downstream in our production, heating and heat treatment furnaces etc (full scope 1-2) as well as all the emission from input material, eg. alloys, scope 3.

Steel Grade	Format	Condition	Scope 1-3 (CO2e kg /1000 kg steel)
SB500	Flat bar	+AR	416
SB280	Round bar	+AR	410
SB280X	Flat bar	+AR	411
SB450	Round bar	+AR	411
SB280XM	Round bar	+AR	429
7256	Round bar	+AR	511
280 M (7266)	Round bar	+AR	516
7255	Flat bar	+AR	513

All above data are to be seen as typical values for the specified format and condition. Detailed information about your specific product please contact your sales contact.

### Other properties (typical values)

Youngs module (GPa)	Poisson 's ratio (-)	Shear module (GPa)	Density (kg/m3)
210	0.3	80	7800
Average CTE 20-300°C (µm/m°K)	Specific heat capacity 50/100°C (J/kg °K)	Thermal conductivity Ambient temperature (W/m°K)	Electrical resistivity Ambient temperature (µΩm)
12	460 - 480	40 - 45	0.20 - 0.25

### Contact us

Would you like to know more about our offers? Don't hesitate to contact us:

Via e-mail: [info@ovako.com](mailto:info@ovako.com)

Via telephone: +46 8 622 1300

For more detailed information please visit <http://www.ovako.com/en/Contact-Ovako/>

### Disclaimer

*The information in this document is for illustrative purposes only. The data and examples are only general recommendations and not a warranty or a guarantee. The suitability of a product for a specific application can be confirmed only by Ovako once given the actual conditions. The purchaser of an Ovako product has the responsibility to ascertain and control the applicability of the products before using them. Continuous development may necessitate changes in technical data without notice. This document is only valid for Ovako material. Other material, covering the same international specifications, does not necessarily comply with the properties presented in this document.*