

25CrMo4 All

General Information

25CrMo4 is a Cr and Mo alloyed quench and tempering steel with low carbon content. The steel combine high strength with high toughness.

322A - is an ingot cast variant .

6014 and 6016 are both M-steel

Delivered as rolled, soft annealed, normalized or quench and tempered. Weldable under certain conditions.

M-Steel®

The basis for the concept is that non-metallic inclusions are modified and controlled with calcium treatment in a way to minimize tool wear and to maximize chip control in machining operations. Our M-Steel treatment can be applied to any steel grade.

Similar designations

SS2225, 4130, 1.7218

Chemical composition

| Variant | Cast | Di | Weldability | | C % | Si % | Mn % | P % | S % | Cr % | Mo % |
|-----------------------|------|-----|-------------------------|-----|------|------|------|-------|-------|------|------|
| 6014, 6016, MoC 210 M | CC | 4.1 | CEV 0.68 _{max} | Min | 0.22 | 0.05 | 0.60 | 0.000 | 0.015 | 0.90 | 0.15 |
| | | | Pcm 0.4 _{max} | Max | 0.29 | 0.40 | 0.90 | 0.025 | 0.035 | 1.20 | 0.30 |

Mechanical Properties

| Variant | Condition ⓘ | Format | Dimension [mm] | Yield strength min [MPa] | Tensile strength [MPa] | Elongation A ₅ [%] | Hardness | Impact (ISO-V) strength _{min} |
|-----------------------|-------------|-----------|----------------|--------------------------|------------------------|-------------------------------|------------|--|
| 6014, 6016, MoC 210 M | +AR | Round bar | 25 < 160 | - | - | - | < 280 HB | - |
| | +A | Round bar | 25 < 160 | - | - | - | < 220 HB | - |
| | +QT | Round bar | 25 < 40 | 600* | 800-950 | 14 | 240-280 HB | -20 °C 27 J (long) |
| | | Round bar | 40 < 100 | 450* | 700-850 | 15 | 200-250 HB | -20 °C 27 J (long) |
| | | Round bar | 100 < 160 | 400* | 650-800 | 16 | 190-240 HB | -20 °C 27 J (long) |

*R_{p0.2} * R_{eh}, ** R_{el}*

Transformation temperatures

| | Temperature °C |
|-----|----------------|
| MS | 391 |
| AC1 | 746 |
| AC3 | 826 |

Heat treatment recommendations

| Treatment | Condition ⓘ | Temperature cycle | Cooling/quenching |
|------------------------------|-------------|-------------------|--------------------------------|
| Hot forging | +AR | 850-1100°C | In still air |
| Normalizing | +N | 840-880°C | In still air |
| Soft annealing | +A | 700-730°C / 3h | In still air |
| Stress relieve annealing | +SRA | 525-620°C | In still air |
| Hardening | +QT | 840-870°C | In oil Temper immediately |
| Hardening | +QT | 820-850°C | In water Temper immediately |
| Induction or Flame hardening | I-F | 850-900°C | Water spray Temper immediately |
| Tempering | +T | 550-675°C | |

Steel cleanliness

| Micro inclusions - steel grade 322A | | | | | | | | | Macro inclusions - 322A | |
|-------------------------------------|-----------|-----|-----|-----|----|----|-----|-----|-------------------------|--------------------------------|
| Applied standard | ASTM E45 | | | | | | | | Applied standard | ISO 3763 (Blue fracture) |
| Sampling | ASTM A295 | | | | | | | | Sampling | Statistical testing on billets |
| Maximum | A | | B | | C | | D | | Limits | < 5 mm/dm ² |
| average | Th | He | Th | He | Th | He | Th | He | | |
| limits | 2.5 | 1.5 | 1.5 | 0.5 | 0 | 0 | 1.0 | 0.5 | | |

SUSTAINABILITY-ENVIRONMENTAL IMPACT DATA

At Ovako sustainability and reduction of our environmental impact is a major focus in everything we do.

Further information is found [here](#).

| Steel works | Hofors | Smedjebacken | Imatra |
|----------------------|--------|--------------|--------|
| CO ₂ e/kg | 120 | 62 | 76 |

To get the full picture of our products environmental impact we have to look at all of our CO₂ emission sources.

Not only the steel work Scope 1-2 itself, but all operations downstream in our production, heating and heat treatment furnaces etc (full scope 1-2) as well as all the emission from input material, eg. alloys, scope 3.

| Steel Grade | Format | Condition | Scope 1-3 (CO ₂ e kg /1000 kg steel) | Climate compensated Net emission = Scope 3 (CO ₂ e kg /1000 kg steel) Scope 1 - 2 = 0 (compensated) |
|-----------------|-----------|-----------|---|--|
| 322A | Round bar | +AR | 619 | 220 |
| 322A | Round bar | +QT | 625 | 224 |
| 322A | Tube,wall | +AR | 643 | 245 |
| 322A | Tube,wall | +QT | 651 | 252 |
| 9224 | Round bar | +AR | 464 | 230 |
| 6014, MoC 210 M | Round bar | +AR | 525 | 244 |
| 6014, MoC 210 M | Round bar | +QT | 779 | 292 |

As of 1 January 2022 we use carbon offset for all our scope 1- 2 emissions, so in practice the climate compensated data is the same as the full Scope 3 level.

All above data are to be seen as typical values for the specified format and condition. Detailed information about your specific product please contact your sales contact.

Other properties (typical values)

| Youngs module (GPa) | Poisson 's ratio (-) | Shear module (GPa) | Density (kg/m ³) |
|-------------------------------|---|--|--|
| 210 | 0.3 | 80 | 7800 |
| Average CTE 20-300°C (µm/m°K) | Specific heat capacity 50/100°C (J/kg °K) | Thermal conductivity Ambient temperature (W/m°K) | Electrical resistivity Ambient temperature (µΩm) |
| 12 | 460 - 480 | 40 - 45 | 0.20 - 0.25 |

Contact us

Would you like to know more about our offers? Don't hesitate to contact us:

Via e-mail: info@ovako.com

Via telephone: +46 8 622 1300

For more detailed information please visit <http://www.ovako.com/en/Contact-Ovako/>

Disclaimer

The information in this document is for illustrative purposes only. The data and examples are only general recommendations and not a warranty or a guarantee. The suitability of a product for a specific application can be confirmed only by Ovako once given the actual conditions. The purchaser of an Ovako product has the responsibility to ascertain and control the applicability of the products before using them. Continuous development may necessitate changes in technical data without notice. This document is only valid for Ovako material. Other material, covering the same international specifications, does not necessarily comply with the properties presented in this document.