

## STEEL GRADE

Last revised: Tue, 28 Jan 2025 16:23:36 GMT

# 30CrNiMo8

All

## General Information

Quenching and tempering steel with a very high hardenability.

For additional Heat Treatment Data, please visit the Heat Treatment Guide

## Similar designations

1.6580, 823M30

## Chemical composition

Variant	Cast	Di		C %	Si %	Mn %	P %	S %	Cr %	Ni %	Mo %	Cu %
30CrNiMo8 ISO 683-2:2016	Std	12.1	Min	0.26	0.10	0.50	-	-	1.80	1.80	0.30	-
			Max	0.34	0.40	0.80	0.025	0.035	2.20	2.20	0.50	0.40

## Mechanical Properties

Variant	Condition <sup>①</sup>	Format	Dimension [mm]	Yield strength min [MPa]	Tensile strength [MPa]	Elongation A <sub>5</sub> [%]	Reduction of area Z <sub>min</sub> [%]	Hardness	Impact (ISO-V) strength <sub>min</sub>
30CrNiMo8 ISO 683-2:2016	+AR	Round bar	25 < 150	-	-	-	-	< 410 HB	-
	+A	Round bar	25 < 150	-	-	-	-	< 248 HB	-
	+QT	Round bar	25 < 40	850	1030-1230	12	40	-	20 °C 30 J (long)
		Round bar	40.1 < 100	800*	980-1180	12	45	-	20 °C 35 J (long)
		Round bar	100.1 < 150	800*	980-1180	12	50	-	20 °C 45 J (long)

*R<sub>p0.2</sub> \* R<sub>eh</sub>, \*\* R<sub>el</sub>*

## Transformation temperatures

	Temperature °C
MS	309
AC1	731
AC3	788

## Heat treatment recommendations

Treatment	Condition <sup>②</sup>	Temperature cycle	Cooling/quenching
Quenching	+QT	830...860	In oil or water
Tempering	+QT	540...660	In air
Annealing	+A	650...700	Slowly (15 °C/h) until 600 °C
Stress relieve annealing	+SRA	450...650	In air
Hot forging		880...1 050	In air

## SUSTAINABILITY-ENVIRONMENTAL IMPACT DATA

At Ovako sustainability and reduction of our environmental impact is a major focus in everything we do.

Further information is found [here](#).

Steel works	Hofors	Smedjebacken	Imatra
CO2e/kg	120	62	76

To get the full picture of our products environmental impact we have to look at all of our CO<sub>2</sub> emission sources.

Not only the steel work Scope 1-2 itself, but all operations downstream in our production, heating and heat treatment furnaces etc (full scope 1-2) as well as all the emission from input material, eg. alloys, scope 3.

Steel Grade	Format	Condition	Scope 1-3 (CO2e kg /1000 kg steel)
6507	Round bar	+AR	811
6507	Round bar	+QT	1121

All above data are to be seen as typical values for the specified format and condition. Detailed information about your specific product please contact your sales contact.

### Other properties (typical values)

Youngs module (GPa)	Poisson´s ratio (-)	Shear module (GPa)	Density (kg/m3)
210	0.3	80	7800
Average CTE 20-300°C (µm/m°K)	Specific heat capacity 50/100°C (J/kg °K)	Thermal conductivity Ambient temperature (W/m°K)	Electrical resistivity Ambient temperature (µΩm)
12	460 - 480	40 - 45	0.20 - 0.25

### Contact us

Would you like to know more about our offers? Don´t hesitate to contact us:

Via e-mail: [info@ovako.com](mailto:info@ovako.com)

Via telephone: +46 8 622 1300

For more detailed information please visit <http://www.ovako.com/en/Contact-Ovako/>

### Disclaimer

*The information in this document is for illustrative purposes only. The data and examples are only general recommendations and not a warranty or a guarantee. The suitability of a product for a specific application can be confirmed only by Ovako once given the actual conditions. The purchaser of an Ovako product has the responsibility to ascertain and control the applicability of the products before using them. Continuous development may necessitate changes in technical data without notice. This document is only valid for Ovako material. Other material, covering the same international specifications, does not necessarily comply with the properties presented in this document.*