

## STEEL GRADE

Last revised: Thu, 30 Jan 2025 10:37:59 GMT

# 40CrMoV4-6

All

**General Information****Similar designations**

ASTM A 193 B16

**Chemical composition**

Variant	Cast		C %	Si %	Mn %	P %	S %	Cr %	Mo %	V %	Al %
6098	CC	Min	0.36	0.15	0.45	-	-	0.80	0.50	0.250	-
		Max	0.44	0.35	0.70	0.025	0.025	1.15	0.65	0.350	0.020

## Mechanical Properties

Variant	Condition	Format	Dimension [mm]	Yield strength min [MPa]	Tensile strength [MPa]	Elongation A <sub>5</sub> [%]	Reduction of area Z <sub>min</sub> [%]	Hardness	Impact (ISO-V) strength <sub>min</sub>
6098	+AR	Round bar	25 < 160	-	-	-	-	< 330 HB	-
	+A		25 < 160	-	-	-	-	< 255 HB	-
	+QT	Round bar	25 < 65	725	860-1000	14	50	250-300 HB	20 °C 30 J (long)
			65 < 100	700	850-1000	14	45	250-300 HB	20 °C 30 J (long)
		Round bar	100 < 160	640	850-1000	14	45	250-300 HB	20 °C 25 J (long)

*R<sub>p0,2</sub> \* R<sub>eh</sub>, \*\* R<sub>el</sub>*


## Transformation temperatures

	Temperature °C
MS	323
AC1	739
AC3	804


## Heat Treatment Guide generated Graphs

The following graphs are generated from a theoretical model. For further info see the Heat treatment guide module. Select a specific grade version for individual display.


Tempering Diagram (hardness)



Tempering Diagram (strength)



# Jominy



## SUSTAINABILITY-ENVIRONMENTAL IMPACT DATA

At Ovako sustainability and reduction of our environmental impact is a major focus in everything we do.

Further information is found [here](#).

Steel works	Hofors	Smedjebacken	Imatra
CO <sub>2</sub> e/kg	120	62	76

To get the full picture of our products environmental impact we have to look at all of our CO<sub>2</sub> emission sources.

Not only the steel work Scope 1-2 itself, but all operations downstream in our production, heating and heat treatment furnaces etc (full scope 1-2) as well as all the emission from input material, eg. alloys, scope 3.

Steel Grade	Format	Condition	Scope 1-3 (CO <sub>2</sub> e kg /1000 kg steel)
6098	Round bar	+AR	544
6098	Round bar	+QT	801

All above data are to be seen as typical values for the specified format and condition. Detailed information about your specific product please contact your sales contact.

### Other properties (typical values)

Youngs module (GPa)	Poisson´s ratio (-)	Shear module (GPa)	Density (kg/m <sup>3</sup> )
210	0.3	80	7800
Average CTE 20-300°C (µm/m°K)	Specific heat capacity 50/100°C (J/kg °K)	Thermal conductivity Ambient temperature (W/m°K)	Electrical resistivity Ambient temperature (µΩm)
12	460 - 480	40 - 45	0.20 - 0.25

### Contact us

Would you like to know more about our offers? Don´t hesitate to contact us:

Via e-mail: [info@ovako.com](mailto:info@ovako.com)

Via telephone: +46 8 622 1300

For more detailed information please visit <http://www.ovako.com/en/Contact-Ovako/>

### Disclaimer

*The information in this document is for illustrative purposes only. The data and examples are only general recommendations and not a warranty or a guarantee. The suitability of a product for a specific application can be confirmed only by Ovako once given the actual conditions. The purchaser of an Ovako product has the responsibility to ascertain and control the applicability of the products before using them. Continuous development may necessitate changes in technical data without notice. This document is only valid for Ovako material. Other material, covering the same international specifications, does not necessarily comply with the properties presented in this document.*