

51SiMoV4-4* All

General Information

51SiMoV4-4* is an alloyed Quench and Tempering steel used in many tool like applications where there is need for high hardness and mechanical strength combined with good toughness.

Similar designations

AISI S2, UNS T41902

Chemical composition

Variant	Cast		C %	Si %	Mn %	P %	S %	Mo %	V %	Cu %
593E	IC	Min	0.48	0.90	0.30	-	-	0.40	0.100	-
		Max	0.55	1.10	0.50	0.010	0.010	0.50	0.200	0.25

Other properties (typical values)

Youngs module (GPa)	Poisson´s ratio (-)	Shear module (GPa)	Density (kg/m ³)
210	0.3	80	7800
Average CTE 20-300°C (µm/m°C)	Specific heat capacity 50/100°C (J/kg °K)	Thermal conductivity Ambient temperature (W/m°C)	Electrical resistivity Ambient temperature (µΩm)
12	460 - 480	40 - 45	0.20 - 0.25

Contact us

Would you like to know more about our offers? Don´t hesitate to contact us:

Via e-mail: info@ovako.com

Via telephone: +46 8 622 1300

For more detailed information please visit <http://www.ovako.com/en/Contact-Ovako/>

Disclaimer

The information in this document is for illustrative purposes only. The data and examples are only general recommendations and not a warranty or a guarantee. The suitability of a product for a specific application can be confirmed only by Ovako once given the actual conditions. The purchaser of an Ovako product has the responsibility to ascertain and control the applicability of the products before using them. Continuous development may necessitate changes in technical data without notice. This document is only valid for Ovako material. Other material, covering the same international specifications, does not necessarily comply with the properties presented in this document.