Last revised: Thu, 30 Jan 2025 11:24:15 GMT

55NiCrMoV7



General Information

55 NiCr MoV7 is an alloyed Quench and Tempering steel used in many tool like applications where there is need for high hardness and mechanical strength combined with good toughness.

BQ-Steel®

BQ-Steel® is a bearing quality clean steel optimized for fatigue strength and is also ideal for new design solutions outside the bearing industry.

Similar designations

55 NCDV 7, L6, 1.2714, UNS T61206

Chemical composition

Variant	Cast	Weldability		С %	Si %	Mn %	Р%	S %	Cr %	Ni %	Мо %	V %
696R	IC	CEV 1.71 _{max}	Min	0.52	0.20	0.70	-	-	1.10	1.50	0.45	0.080
		Pcm 0.74 _{max}	Max	0.56	0.40	0.90	0.025	0.005	1.30	1.80	0.55	0.120


Transformation temperatures

	Temperature °C				
MS	237				
AC1	716				
AC3	772				


Heat Treatment Guide generated Graphs

The following graphs are generated from a theoretical model. For further info see the Heat treatment guide module. Select a specific grade version for individual display.

Tempering Diagram (hardness)




Tempering Diagram (strength)



Tempering temperature (°C)

Jominy



SUSTAINABILITY-ENVIRONMENTAL IMPACT DATA

At Ovako sustainability and reduction of our environmental impact is a major focus in everything we do.

Further information is found here.

Steel works	Hofors	Smedjebacken	Imatra
CO2e/kg	120	62	76

To get the full picture of our products environmental impact we have to look at all of our CO₂ emission sources.

Not only the steel work Scope 1-2 itself, but all operations downstream in our production, heating and heat treatment furnaces etc (full scope 1-2) as well as all the emission from input material, eg. alloys, scope 3.

Steel Grade	Format			Climate compensated Net emission = Scope 3 (CO2e kg /1000 kg steel) Scope 1 - 2 = 0 (compensated)				
696R	Round bar	+AR	893	494				
696R	Round bar	+N	899	498				
696R	Tube,wall	+AR	932	531				
696R	Tube,wall	+N	934	531				

All above data are to be seen as typical values for the specified format and condition. Detailed information about your specific product please contact your sales contact.

Other properties (typical values)

Youngs module (GPa)	Poisson's ratio (-)	Shear module (GPa)	Density (kg/m3)	
210	0.3	80	7800	
Average CTE 20- 300°C (µm/m°K)	Specific heat capacity 50/100°C (J/kg °K)	Thermal conductivity Ambient temperature (W/m°K)	Electrical resistivityAmbient temperature (μΩm)	
12	460 - 480	40 - 45	0.20 - 0.25	

Contact us

Would you like to know more about our offers? Don't hesitate to contact us:

Via e-mail: info@ovako.com

Via telephone: +46 8 622 1300

For more detailed information please visit http://www.ovako.com/en/Contact-Ovako/

Disclaimer

The information in this document is for illustrative purposes only. The data and examples are only general recommendations and not a warranty or a guarantee. The suitability of a product for a specific application can be confirmed only by Ovako once given the actual conditions. The purchaser of an Ovako product has the responsibility to ascertain and control the applicability of the products before using them. Continuous development may necessitate changes in technical data without notice. This document is only valid for Ovako material. Other material, covering the same international specifications, does not necessarily comply with the properties presented in this document.