Last revised: Thu, 30 Jan 2025 10:31:23 GMT

38MnMo6-3



General Information

M-Steel®

The basis for the concept is that non-metallic inclusions are modified and controlled with calcium treatment in a way to minimize tool wear and to maximize chip control in machining operations. Our M-Steel treatment can be applied to any steel grade.

Similar designations

709A40, 709H40, 709M40

Chemical composition

Variant	Cast	Di		С %	Si %	Mn %	Р %	s %	Cr %	Mo %
605M36, 5905 (M)	CC 5	5 Min Max	Min	0.32	0.10	1.30	-	-	0.10	0.22
			0.40	0.35	1.70	0.035	0.040	0.30	0.30	

Mechanical Properties

Variant	Condition	Format	Dimension [mm]	Yield strength min [MPa]	Tensile strength [MPa]	Elongation A ₅ [%]	Hardness	Impact (ISO- V) strength _{min}
605M36, 5905 (M)	+AR	Round bar	25 < 160	-	-	-	< 300 HB	-
		Round bar	< 160	525	700-850	17	201-255 HB	20 °C 50 J (long)
	+QT	All formats	< 140	570	775-925	15	223-277 HB	20 °C 50 J (long)
	+01	Round bar	< 120	680	850-1000	13	248-302 HB	20 °C 50 J (long)
		Round bar	< 90	740	925-1075	12	269-331 HB	20 °C 42 J (long)

 $Rp_{0.2} * R_{eh}$, ** R_{el}


Transformation temperatures

	Temperature °C				
MS	310				
AC1	734				
AC3	782				


Heat Treatment Guide generated Graphs

The following graphs are generated from a theoretical model. For further info see the Heat treatment guide module. Select a specific grade version for individual display.


Tempering Diagram (hardness)



Tempering Diagram (strength)



Jominy



SUSTAINABILITY-ENVIRONMENTAL IMPACT DATA

At Ovako sustainability and reduction of our environmental impact is a major focus in everything we do.

Further information is found here.

Steel works	Hofors	Smedjebacken	Imatra
CO2e/kg	120	62	76

To get the full picture of our products environmental impact we have to look at all of our CO₂ emission sources

Not only the steel work Scope 1-2 itself, but all operations downstream in our production, heating and heat treatment furnaces etc (full scope 1-2) as well as all the emission from input material, eg. alloys, scope 3.

Steel Grade	Format	Scope 1-3 (CO2e k /1000 kg steel)		Climate compensated Net emission = Scope 3 (CO2e kg /1000 kg steel) Scope 1 - 2 = 0 (compensated)				
605M36, 5905 (M)	Round bar	+AR	517	235				
605M36, 5905 (M)	Round bar	+QT	769	282				

All above data are to be seen as typical values for the specified format and condition. Detailed information about your specific product please contact your sales contact.

Other properties (typical values)

Youngs module (GPa)	Poisson's ratio (-)	Shear module (GPa)	Density (kg/m3)
210	0.3	80	7800
Average CTE 20- 300°C (µm/m°K)	Specific heat capacity 50/100°C (J/kg °K)	Thermal conductivity Ambient temperature (W/m°K)	Electrical resistivityAmbient temperature (μΩm)
12	460 - 480	40 - 45	0.20 - 0.25

Contact us

Would you like to know more about our offers? Don't hesitate to contact us:

Via e-mail: info@ovako.com

Via telephone: +46 8 622 1300

For more detailed information please visit http://www.ovako.com/en/Contact-Ovako/

Disclaimer

The information in this document is for illustrative purposes only. The data and examples are only general recommendations and not a warranty or a guarantee. The suitability of a product for a specific application can be confirmed only by Ovako once given the actual conditions. The purchaser of an Ovako product has the responsibility to ascertain and control the applicability of the products before using them. Continuous development may necessitate changes in technical data without notice. This document is only valid for Ovako material. Other material, covering the same international specifications, does not necessarily comply with the properties presented in this document