MATERIAL DATA SHEET STEEL GRADE

Last revised: Fri, 31 Jan 2025 15:13:37 GMT



C60E AII

General Information

Ovako 061 is an ingot casted steel of BQ (Bearing Quality). High hardness (approx. 60HRC) and high strength can be achieved after hardening due to the relatively high carbon content. The steel is suitable for various type of applications where high strength is needed. The steel grade fulfils most of the C60E standard and have a tighter composition range in order to have consistent properties

BQ-Steel®

BQ-Steel® is a bearing quality clean steel optimized for fatigue strength and is also ideal for new design solutions outside the bearing industry.

Similar designations

1.1221, ASTM/SAE 1060

Chemical composition

Variant	Cast	Weldability		С%	Si %	Mn %	Р%	S %	Cr %	Ni %	Mo %	DI %
0614		CEV 0.82 _{max}	Min	0.58	0.05	0.55	-	-	0.15	-	-	1.40
UUTA		Pcm 0.69 _{max}	Max	0.61	0.15	0.65	0.020	0.007	0.22	0.15	0.08	1.60
C60E EN 10082 2:2006 rof	Std	CEV max	Min	0.57	-	0.60	-	-	-	-	-	-
CODE EN 10083-2.2000 TEL	Siu	Pcm _{max}	Max	0.65	0.40	0.90	0.030	0.035	0.40	0.40	0.10	-

Transformation temperatures

	Temperature °C				
MS	271				
AC1	720				
AC3	746				

Heat Treatment Guide generated Graphs

The following graphs are generated from a theoretical model. For further info see the Heat treatment guide module. Select a specific grade version for individual display.



Tempering Diagram (hardness)

Tempering temperature (°C)

Tempering Diagram (strength)



Tempering temperature (°C)

Jominy



Hardenability



Steel cleanliness

Micro inclusions								Aacro inclusions			
Applied standard	ASTM E45								Applied standard	ISO 3763 (Blue fracture)	
Sampling	ASTN	ASTM A295							Sampling	Statistical testing on billets	
Maximum average	A B C			D							
limits	Th	He	Th	He	Th	He	Th	Не	Limits	< 2,5 mm/dm ²	
	2,0	1,5	0,5	0,1	0	0	0,2	0,1			

SUSTAINABILITY-ENVIRONMENTAL IMPACT DATA

At Ovako sustainability and reduction of our environmental impact is a major focus in everything we do.

Further information is found here.

Steel works	Hofors	Smedjebacken	Imatra
CO2e/kg	120	62	76

To get the full picture of our products environmental impact we have to look at all of our CO_2 emission sources.

Not only the steel work Scope 1-2 itself, but all operations downstream in our production, heating and heat treatment furnaces etc (full scope 1-2) as well as all the emission from input material, eg. alloys, scope 3.

Steel Grade	Format	G Condition	Scope 1-3 (CO2e kg /1000 kg steel)	Climate compensated Net emission = Scope 3 (CO2e kg /1000 kg steel) Scope 1 - 2 = 0 (compensated)
061A	Round bar	+AR	569	170
061A	Round bar	+QT	574	173
061A	Tube,wall	+AR	587	190
061A	Tube,wall	+QT	596	196

All above data are to be seen as typical values for the specified format and condition. Detailed information about your specific product please contact your sales contact.

Other properties (typical values)

Youngs module (GPa)	Poisson´s ratio (-)	Shear module (GPa)	Density (kg/m3)
210	0.3	80	7800
Average CTE 20- 300°C (µm/m°K)	Specific heat capacity 50/100°C (J/kg °K)	Thermal conductivity Ambient temperature (W/m°K)	Electrical resistivityAmbient temperature (μΩm)
12	460 - 480	40 - 45	0.20 - 0.25

Contact us

Would you like to know more about our offers? Don't hesitate to contact us:

Via e-mail: info@ovako.com

Via telephone: +46 8 622 1300

For more detailed information please visit http://www.ovako.com/en/Contact-Ovako/

Disclaimer

The information in this document is for illustrative purposes only. The data and examples are only general recommendations and not a warranty or a guarantee. The suitability of a product for a specific application can be confirmed only by Ovako once given the actual conditions. The purchaser of an Ovako product has the responsibility to ascertain and control the applicability of the products before using them. Continuous development may necessitate changes in technical data without notice. This document is only valid for Ovako material. Other material, covering the same international specifications, does not necessarily comply with the properties presented in this document.