

MATERIAL DATA SHEET

STEEL GRADE

Last revised: Fri, 31 Jan 2025 15:13:37 GMT

OVAKO

C60E All

General Information

Ovako 061 is an ingot casted steel of BQ (Bearing Quality). High hardness (approx. 60HRC) and high strength can be achieved after hardening due to the relatively high carbon content. The steel is suitable for various type of applications where high strength is needed. The steel grade fulfils most of the C60E standard and have a tighter composition range in order to have consistent properties

Similar designations

1.1221, ASTM/SAE 1060


Chemical composition

Variant	Cast		C %	Si %	Mn %	P %	S %	Cr %	Ni %	Mo %
C60E EN 10083-2:2006 ref	Std	Min	0.57	-	0.60	-	-	-	-	-
		Max	0.65	0.40	0.90	0.030	0.035	0.40	0.40	0.10

Transformation
temperatures

	Temperature °C
MS	271
AC1	720
AC3	746

Hardenability



Steel cleanliness

Micro inclusions									Macro inclusions	
Applied standard	ASTM E45								Applied standard	ISO 3763 (Blue fracture)
Sampling	ASTM A295								Sampling	Statistical testing on billets
Maximum average limits	A		B		C		D		Limits	< 2,5 mm/dm ²
	Th	He	Th	He	Th	He	Th	He		
	2,0	1,5	0,5	0,1	0	0	0,2	0,1		

SUSTAINABILITY-ENVIRONMENTAL IMPACT DATA

At Ovako sustainability and reduction of our environmental impact is a major focus in everything we do.

Further information is found [here](#).

Steel works	Hofors	Smedjebacken	Imatra
CO ₂ e/kg	120	62	76

To get the full picture of our products environmental impact we have to look at all of our CO₂ emission sources.

Not only the steel work Scope 1-2 itself, but all operations downstream in our production, heating and heat treatment furnaces etc (full scope 1-2) as well as all the emission from input material, eg. alloys, scope 3.

Steel Grade	Format	Condition ①	Scope 1-3 (CO ₂ e kg /1000 kg steel)	Climate compensated Net emission = Scope 3 (CO ₂ e kg /1000 kg steel) Scope 1 - 2 = 0 (compensated)
061A	Round bar	+AR	569	170
061A	Round bar	+QT	574	173
061A	Tube,wall	+AR	587	190
061A	Tube,wall	+QT	596	196

All above data are to be seen as typical values for the specified format and condition. Detailed information about your specific product please contact your sales contact.

Other properties (typical values)

Youngs module (GPa)	Poisson's ratio (-)	Shear module (GPa)	Density (kg/m ³)
210	0.3	80	7800
Average CTE 20-300°C (µm/m°K)	Specific heat capacity 50/100°C (J/kg °K)	Thermal conductivity Ambient temperature (W/m°K)	Electrical resistivity Ambient temperature (µΩm)
12	460 - 480	40 - 45	0.20 - 0.25

Contact us

Would you like to know more about our offers? Don't hesitate to contact us:

Via e-mail: info@ovako.com

Via telephone: +46 8 622 1300

For more detailed information please visit <http://www.ovako.com/en/Contact-Ovako/>

Disclaimer

The information in this document is for illustrative purposes only. The data and examples are only general recommendations and not a warranty or a guarantee. The suitability of a product for a specific application can be confirmed only by Ovako once given the actual conditions. The purchaser of an Ovako product has the responsibility to ascertain and control the applicability of the products before using them. Continuous development may necessitate changes in technical data without notice. This document is only valid for Ovako material. Other material, covering the same international specifications, does not necessarily comply with the properties presented in this document.