# Material data sheet Steel grade



# S275JR All

### **General Information**

S275JR belongs to the group of none alloyed structural steels

## Similar designations

St 44-2, SS1414, SS 141412-00

## Chemical composition

Variant	Cast		С %	Si %	Mn %	P %	s %	Cu %	N %
SB1412	СС	Min	-	-	-	-	-	-	-
		Max	0.21	0.40	1.50	0.040	0.040	0.55	0.0120

# **Mechanical Properties**

Variant	6 Condition	Format	Dimension [mm]	Yield strength min [MPa]	Tensile strength [MPa]	Elongation A <sub>5</sub> [%]
SB1412	+AR	Flat bar	< 16	275*	410-560	22
		Flat bar	17 < 40	265*	410-560	22
		Flat bar	41 < 63	255*	410-560	21
		Flat bar	64 < 80	245*	410-560	20

 $Rp_{0.2} * R_{eh}$ , \*\*  $R_{el}$ 

# Transformation temperatures

	Temperature °C			
MS	485			
AC1	725			
AC3	863			

#### SUSTAINABILITY-ENVIRONMENTAL IMPACT DATA

At Ovako sustainability and reduction of our environmental impact is a major focus in everything we do.

Further information is found here.

In many international comparisons the crude steel Scope 1-2 emission is a key parameter, ie. the  $CO_2$  emission from the steel works itself.

As of 1 January 2022 we carbon offset all our scope 1 and 2 volume shown below.

Steel works	Hofors	Smedjebacken	Imatra
CO2e/kg	120	62	76

To get the full picture of our products environmental impact we have to look at all of our  $CO_2$  emission sources.

Not only the steel work Scope 1-2 itself, but all operations downstream in our production, heating and heat treatment furnaces etc (full scope 1-2) as well as all the emission from input material, eg. alloys, scope 3.

Steel Grade	Formati			Climate compensated Net emission = Scope 3 (CO2e kg /1000 kg steel) Scope 1 - 2 = 0 (compensated)		
SB1412	Flat bar	+AR	359	174		

As of 1 January 2022 we use carbon offset for all our scope 1- 2 emissions, so in practice the climate compensated data is the same as the full Scope 3 level.

All above data are to be seen as typical values for the specified format and condition. Detailed information about your specific product please contact your sales contact.

### Other properties (typical values)

Youngs module (GPa)	Poisson's ratio (-)	Shear module (GPa)	Density (kg/m3)
210	0.3	80	7800
Average CTE 20- 300°C (µm/m°K)	Specific heat capacity 50/100°C (J/kg °K)	Thermal conductivity Ambient temperature (W/m°K)	Electrical resistivityAmbient temperature (μΩm)
12	460 - 480	40 - 45	0.20 - 0.25

#### Contact us

Would you like to know more about our offers? Don't hesitate to contact us:

Via e-mail: info@ovako.com

Via telephone: +46 8 622 1300

For more detailed information please visit http://www.ovako.com/en/Contact-Ovako/

### **Disclaimer**

The information in this document is for illustrative purposes only. The data and examples are only general recommendations and not a warranty or a guarantee. The suitability of a product for a specific application can be confirmed only by Ovako once given the actual conditions. The purchaser of an Ovako product has the responsibility to ascertain and control the applicability of the products before using them. Continuous development may necessitate changes in technical data without notice. This document is only valid for Ovako material. Other material, covering the same international specifications, does not necessarily comply with the properties presented in this document.